

Akustikabsorber

PT FIREABSORBER

M1 Fire resistant Polyurethane foam for absorption purpose.



Measurements according to UNE-EN ISO 140-3 standard (December 1995)
Acoustic Isolation of Construction Materials in Laboratory Measurements.
Corresponds completely with ISO 140-3(1995) standard.
Cancels and substitutes UNE 74-040/3 (1984) standard.
Calculations according to NBCEA88.

Tipo	Codice	autoadesive	Rw (dB)	Peso (kg.)
PT-30 FIREABSORBER	26331	-	9	0,75
PT-30A FIREABSORBER	26333	x	9	0,75
PT-50 FIREABSORBER	26332	-	6	0,75
PT-50A FIREABSORBER	26334	x	6	0,75

CARATTERISTICHE TECNICHE

— Composition

M1 Fire resistant Polyurethane foam for absorption purpose.

— Thicknesses

30mm 50mm

FORMATS

— Sheets

1000x1000 mm

APPLICAZIONI

Aislante térmico, comportamiento M-1 ignífugo, muy buen absorbente acústico, muy buena resistencia al desgarro.

Akustikabsorber

PT FIREABSORBER

PROPRIETÀ ACUSTICHE

