

Akustikabsorber

VISCOELASTIC LAYERS



Rubber elastomer compound mixed with Barite.

Measurements according to UNE-EN ISO 140-3 standard (December 1995)
Acoustic Isolation of Construction Materials in Laboratory Measurements.
Corresponds completely with ISO 140-3(1995) standard.
Cancels and substitutes UNE 74-040/3 (1984) standard.
Calculations according to NBCEA88.

Tipo	Codice	autoadesive	125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz	Peso (kg)
MP5 A	26603	□	9	11	16	15	16	18	5
MP10 A	26604	□	11	13	17	17	18	26	10
MP5 AA	26605	□	9	11	16	15	16	18	5
MP10 AA	26606	□	11	13	17	17	18	26	10

CARATTERISTICHE TECNICHE

— Composition

Rubber elastomer compound mixed with Barite.

— Thicknesses

2mm 4mm

FORMATS

— Sheets

1230x1030 mm

APPLICAZIONI

Riduzione del rumore diretta di elementi metallici.

Akustikabsorber

VISCOELASTIC LAYERS

PROPRIETÀ ACUSTICHE

