

Akustikabsorber

PS BLACK



Black PU film and absorbing polyurethane foam.

Measurements according to UNE-EN ISO 140-3 standard (December 1995)
Acoustic Isolation of Construction Materials in Laboratory Measurements.
Corresponds completely with ISO 140-3(1995) standard.
Cancels and substitutes UNE 74-040/3 (1984) standard.
Calculations according to NBCEA88.

Tipo	Codice	autoadesive	Rw (dB)	Peso (kg)
PS-15 plancha	26001	-	12	0,463
PS-15 A plancha	26087	x	12	0,463
PS-15 rollo	26010	-	12	0,463
PS-15 A rollo	26068	x	12	-
PS-25 plancha	26004	-	12	0,765
PS-25 A plancha	26088	x	12	0,765
PS-25 rollo	26012	-	12	0,765
PS-25 A rollo	26090	x	12	0,765
PS-40 plancha	26007	-	17	1,218
PS-40 A plancha	26089	x	17	1,218
PS-40 rollo	26014	-	17	1,218
PS-40 A rollo	26091	x	17	1,218

CARATTERISTICHE TECNICHE

— Composition

Black PU film and absorbing polyurethane foam.

— Thicknesses

15mm 25mm 40mm

FORMATS

— Sheets

1200x1000 mm
15mm thick, 8 Sheets per box.
25mm thick, 5 Sheets per box.
40mm thick, 3 Sheets per box.

— Rolls

15mm thick, 1500mm wide x approx. 20m long
25mm thick, 1500mm wide x approx. 20m long
40mm thick, 1500mm wide x approx. 15m long

APPLICAZIONI

Revestimiento absorbente de cabinas insonorizadas o de vehículos donde exista un peligro de empape de hidrocarburos o agua del material absorbente.

Akustikabsorber

PS BLACK

PROPRIETÀ ACUSTICHE

