

Akustikabsorber

PAI



Aluminium facing with fibreglass support and absorbing polyurethane foam.

Measurements according to UNE-EN ISO 140-3 standard (December 1995) Acoustic Isolation of Construction Materials in Laboratory Measurements. Corresponds completely with ISO 140-3(1995) standard. Cancels and substitutes UNE 74-040/3 (1984) standard. Calculations according to NBECA88.

| Tipo | Codice | autoadesive | Rw (dB) | Peso (kg.) |
|------------------|--------|-------------|---------|------------|
| PAI-15 plancha | 26025 | - | 17 | 0,853 |
| PAI-15 A plancha | 26170 | x | 17 | 1,113 |
| PAI-15 rollo | 26022 | - | 17 | 0,853 |
| PAI-15 A rollo | 26172 | x | 17 | 1,113 |
| PAI-25 plancha | 26026 | - | 19 | 1,155 |
| PAI-25 A plancha | 26127 | x | 19 | - |
| PAI-25 rollo | 26023 | - | 19 | 1,155 |
| PAI-25 A rollo | 26173 | x | 19 | 1,415 |
| PAI-40 plancha | 26027 | - | 19 | 1,608 |
| PAI-40 A plancha | 26171 | x | 19 | 1,868 |
| PAI-40 rollo | 26024 | - | 19 | 1,608 |
| PAI-40 A rollo | 26174 | x | 19 | 1,868 |

CARATTERISTICHE TECNICHE

— Composition

Aluminium facing with fibreglass support and absorbing polyurethane foam.

— Thicknesses

15mm 25mm 40mm

FORMATS

— Sheets

1200x1000 mm
15mm thick, 8 Sheets per box.
25mm thick, 5 Sheets per box.
40mm thick, 3 Sheets per box.

— Rolls

1500mm wide x approx. 20m long

APPLICAZIONI

Thermal insulation, M-1 class fire-resistant, good resistance to hydrocarbon damage and not very good acoustic absorber but good isolator.

Akustikabsorber **PAI**

PROPRIETÀ ACUSTICHE

