

Akustikabsorber

AGLO FAR



Black unwoven film and bound polyurethane foam with a density of 150 Kr/m3.

Measurements according to UNE-EN ISO 140-3 standard (December 1995) Acoustic Isolation of Construction Materials in Laboratory Measurements. Corresponds completely with ISO 140-3(1995) standard. Cancels and substitutes UNE 74-040/3 (1984) standard. Calculations according to NBCEA88.

| Tipo | Codice | autoadesive | Rw (dB) | Peso (kg.) |
|------------------------|--------|-------------|---------|------------|
| AGLO FAR 150/20 | 28304 | - | 21 | 3 |
| AGLO FAR + AUTO 150/20 | 28306 | x | 21 | 3 |
| AGLO FAR 150/40 | 28305 | - | 18 | 6 |
| AGLO FAR + AUTO 150/40 | 28307 | x | 18 | 6 |

CARATTERISTICHE TECNICHE

— Composition

Black unwoven film and bound polyurethane foam with a density of 150 Kr/m3.

— Thicknesses

20mm 40mm

FORMATS

— Sheets

2000x1000 mm

— Rolls

Consult for roll manufacturing.

APPLICAZIONI

Revestimiento interior de cabinas insonorizadas o de vehículos, buena absorción.

Akustikabsorber

AGLO FAR

PROPRIETÀ ACUSTICHE

