



Fiberglass facing and M-1 class fireresistant absorbing polyurethane foam.

Measurements according to UNE-EN ISO 140-3 standard (December 1995)  
Acoustic Isolation of Construction Materials in Laboratory Measurements.  
Corresponds completely with ISO 140-3(1995) standard.  
Cancels and substitutes UNE 74-040/3 (1984) standard.  
Calculations according to NBECA88.

Type	Code	SELF-ADHESIVE	Rw (dB)	Weight /m2 (kg)
FI-15 sheet	26206	-	22	1,335
FI-15 A sheet	26201		22	1,335
FI-25 sheet	26207	-	23	2,085
FI-25 A sheet	26205		23	2,085

## TECHNICAL CHARACTERISTICS

### — Composition

Fiberglass facing and M-1 class fireresistant absorbing polyurethane foam.

### — Thicknesses

15mm 25mm

## FORMATS

### — Sheets

1200x1000 mm  
15mm thick, 8 Sheets per box.  
25mm thick, 5 Sheets per box.


## APPLICATIONS

Thermal insulation, M-1 class fire-resistant behaviour, good resistance to hydrocarbon damage and not very good acoustic absorber but good isolator.

ACOUSTIC PROPERTIES

Transmission Loss (dB)

FAI



Absorption coefficient

FAI

