

# Akustikabsorber

## FAIM



Aluminium facing with fibreglass support, M- 1 class fire-resistant absorbing polyurethane foam and 5 Kg/m<sup>2</sup> heavy viscoelastic mass.

Measurements according to UNE-EN ISO 140-3 standard (December 1995)  
Acoustic Isolation of Construction Materials in Laboratory Measurements.  
Corresponds completely with ISO 140-3(1995) standard.  
Cancels and substitutes UNE 74-040/3 (1984) standard.  
Calculations according to NBCEA88.

Type	Code	SELF-ADHESIVE	Rw (dB)	Weight (kg.)
FAIM-15 sheet	26271	-	22	7,335
FAIM-15 A sheet	26273	x	22	7,335
FAIM-25 sheet	26272	-	25	8,085
FAIM-25 A sheet	26274	x	25	8,085

### TECHNICAL CHARACTERISTICS

#### — Composition

Aluminium facing with fibreglass support, M- 1 class fire-resistant absorbing polyurethane foam and 5 Kg/m<sup>2</sup> heavy viscoelastic mass

#### — Thicknesses

15mm 25mm

### FORMATS

#### — Sheets

1200x1000 mm  
15mm thick, 8 Sheets per box.  
25mm thick, 5 Sheets per box.

### APPLICATIONS

Thermal insulation, M-1 class fire-resistant, good resistance to hydrocarbon damage and not very good acoustic absorber but good absorbing isolator with M-1 class fire-resistant behaviour and damping sheet that increases the mass and dampens vibrations.

# Akustikabsorber

## FAIM

### ACOUSTIC PROPERTIES

