

Akustikabsorber

PAI



Aluminium facing with fibreglass support and absorbing polyurethane foam.

Measurements according to UNE-EN ISO 140-3 standard (December 1995) Acoustic Isolation of Construction Materials in Laboratory Measurements. Corresponds completely with ISO 140-3(1995) standard. Cancels and substitutes UNE 74-040/3 (1984) standard. Calculations according to NBCEA88.

Type	Code	SELF-ADHESIVE	Rw (dB)	Weight (kg.)
PAI-15 sheet	26025	-	17	0,853
PAI-15 A sheet	26170	x	17	1,113
PAI-15 roll	26022	-	17	0,853
PAI-15 A roll	26172	x	17	1,113
PAI-25 sheet	26026	-	19	1,155
PAI-25 A sheet	26127	x	19	-
PAI-25 roll	26023	-	19	1,155
PAI-25 A roll	26173	x	19	1,415
PAI-40 sheet	26027	-	19	1,608
PAI-40 A sheet	26171	x	19	1,868
PAI-40 roll	26024	-	19	1,608
PAI-40 A roll	26174	x	19	1,868

TECHNICAL CHARACTERISTICS

— Composition

Aluminium facing with fibreglass support and absorbing polyurethane foam.

— Thicknesses

15mm 25mm 40mm

FORMATS

— Sheets

1200x1000 mm
15mm thick, 8 Sheets per box.
25mm thick, 5 Sheets per box.
40mm thick, 3 Sheets per box.

— Rolls

1500mm wide x approx. 20m long

APPLICATIONS

Thermal insulation, M-1 class fire-resistant, good resistance to hydrocarbon damage and not very good acoustic absorber but good isolator.

Akustikabsorber

PAI

ACOUSTIC PROPERTIES

